



P'F

FINISHING PLASTER PASTE MANUAL OR MECHANICAL APPLICATION

TECHNICAL DEFINITION.

Interior finishing plaster. Can be used with Airless spray. It provides a fine, uniform and even finish and is easy to sand.

COMPOSITION AND APPEARANCE.

Water, calcium carbonate, resin and various additives. The resulting paste is off-white in colour.

SUITABLE SUBSTRATES.

All types of interior substrates: concrete, cellular concrete, cement, breeze block, brick, plasterboard, plaster tiles, plaster, old paint.

COVERINGS.

- Primer coat.
- Paint.
- Wall coverings.

REFERENCE DOCUMENTS.

- DTU 59.1.
- EN 16566.

TECHNICAL PROPERTIES.

- Density: 1.8
- Dry extract: 73 %.

PACKAGING.

15 kg bucket on wrapped pallet.

STORAGE.

18 months in original unopened packaging away from frost and high temperatures.

INSTRUCTIONS FOR USE

PRECAUTIONS FOR USE.

The temperature during application and drying must be between 8° C and 35° C.

Do not apply at a humidity level above 70 %. Do not use on a damp substrate. Do not apply to overheated substrates.

PREPARATION OF SUBSTRATES.

Substrates must comply with the DTU 59.1 standard i.e. be dry, clean, dust-free, hard and free of any trace of separating agent.

Scrape, brush and remove dust from concrete, plasterboard and plaster tiles.

APPLICATION.

MANUAL APPLICATION: With a trowel or filling knife.

MECHANICAL APPLICATION: Airless and spraying machine.

In cold weather, mix the product quickly to aid aspiration.

We recommend removing the filter from the pump, spraying at about 80 cm from the substrate.

After spraying, carefully smooth, e.g. using a 60 cm blade.

Minimum Airless pump capacity 5 L/min (nozzle 527 to 531).

The maximum thickness will be 2 mm per coat. Clean tools with water.

COVERAGE.

Approximately 0.4 to 0.8 kg/m².

DRYING TIME.

Approximately 4-8 hours, depending on the thickness, substrate and ambient conditions.

FINISHING PLASTER PASTE

Plaster usable with
Airless spray.

It provides a fine,
uniform and even finish
and is easy to sand.

ADVANTAGES

- Very versatile.
- Very nice finish, ideal before painting.
- Easy to sand.

AFNOR classification NFT 36.005
Family III - Class 2.

