

CE 86 PATE

READY MIXED JOINT COMPOUND FOR ROUNDED-EDGE PLASTERBOARD JOINTS WITHOUT TAPING

TECHNICAL DEFINITION.

Ready mixed joint compound specially formulated for interior use on round edged plasterboard joints (quality Q1 to Q4).

Also allows for the filling of taper edged plasterboard with sealing tape. Also suitable for all filling and smoothing work before finishing.

COMPOSITION AND APPEARANCE.

Water, calcium carbonate, emulsion resin, extender, and various additives. The resulting paste is white.

SUITABLE SURFACES.

Interior walls and ceilings:

- Plaster. Plaster boards.
- Aerated concrete.
 Concrete.
- Cement.
- Old paintwork.
- Old tiling.

COVERING.

Once the sealant is completely dry it can be covered by all types of paints, plaster-based sealants, and wallpaper paste.

REFERENCE DOCUMENTS.

- DTU 25.41. EN 13963. CE marking.
- DTU 59.1: Building painting work.
- EN 16566: paint sealants for interior work.

TECHNICAL FEATURES.

- Second coat time: 12-48 hours depending on work.
- Paste density: 1.50 kg/L.
- 4-point bending: > 30 daN.
- Adhesion: > 0.5 MPa complies with EN 16566.
- Reaction to fire: A2s1dO.

PRECAUTIONS FOR USE.

The temperature on application and during drying must be between +5 and +30°C. Do not apply at a humidity levels above 70 %. Do not apply on damp surfaces. Do not use paste that has begun to set. Do not inhale dust while sanding



SAFETY.

Safety data sheet available on www.quickfds.com. Please read it before use. Keep out of reach of children. In the event of swallowing, immediately consult a doctor and show him or her the packaging or label. Wearing gloves is recommended

EUH 208 Contains 1,2-benzisothiazol-3(2H)-one and a mixture of: 5-chloro-2-methyl-2H-isothiazol-3-one [EC No. 247-500-7]; 2-methyl-2H-isothiazol-3-one [EC No. 220-239-6] (3:1)(55965-84-9). May trigger an allergic reaction

PREPARATION OF SUBSTRATES.

Substrates must comply with DTU, i.e. be clean, dry, hard, cohesive, dust-free and free of any trace of formwork oil.

For round edged plaster board, allow a clearance of 5 mm between two boards for a better mechanical performance.

The edges of the cut-to-size boards must be bevelled and dusted with a damp sponge.

THICKNESS OF APPLICATION. Max 5 mm.

CONSUMPTION.

- Plasterboard seal:
 between 350 and 750
- between 250 and 350 g/m of plasterboard.
- Coating/smoothing: from 0.250 to 1 kg/m²/mm thickness.

APPLICATION TYPE.

Apply with a plaster knife or smoothing trowel. Clean tools dry or with water if necessary.

DRYING TIME

Depends on surface, weather conditions and application thickness.

PACKAGING.

10 kg and 20 kg buckets.

STORAGI

9 months in original, unopened packaging away from frost and high temperatures.

EMISSIONS IN INTERIOR AIR.

VOC Content: <1 g/L.

ADVANTAGES

- Easy to use.
- Multiple surfaces.
- Easy to sand.
- Excellent adhesion.











