



AIRLESS EXTER

READY-TO-USE SURFACING PLASTER

INTERIOR-EXTERIOR

TECHNICAL DEFINITION.

Ready-to-use plaster for interior and exterior surfacing.

COMPOSITION AND APPEARANCE.

Water, calcium carbonate, emulsion resin, dispersant and various adjuvants.

PERMISSIBLE SUBSTRATES.

Poured concrete, aerated concrete, floor slabs, bricks, cinder block, masonry substrates, painted substrates.

COATING.

All types of plasters, paint and wall coatings

The product is sensitive to UV light and must be covered when used outdoors.

DOCUMENTS TO BE CONSULTED.

- DTU 59.1: Building painting work
- EN 16566: paint plasters for interior work

TECHNICAL FEATURES.

- Second application: 12-72 hours, according to the work.
- Paste density: 1.86 kg/L.
- Adhesion: >0.8 MPa in compliance with EN 16566.

PRECAUTIONS FOR USE.

The temperature on application and during drying must be between +8°C and +35°C. Do not apply when relative humidity >70%. Do not apply to damp substrates. Do not apply to overheated substrates. Safety goggles should be worn when spraying

SAFETY.

A safety data sheet is available at www.quickfds.com. It should be read before use.

Keep out of reach of children.

If swallowed, seek medical advice immediately and show the doctor the packaging or label.

The wearing of gloves and safety goggles is recommended.

PREPARATION OF SUBSTRATES.

Substrates must comply with DTUs, i.e. be clean, dry, hard, cohesive, sound, dust-free and free of any trace of formwork oil.

APPLICATION THICKNESS.

1 to 5 mm.

CONSUMPTION.

Variable depending on the thickness applied: from 1 kg to 3 kg/m² and per layer.

TYPE OF APPLICATION.

Apply first coat manually or mechanically, smooth with a blade.

With a light grip, tighten the plaster from a very shallow angle to remove any ribs and bubbling.

Use the same method for the second layer, leaving as few imperfections as possible.

After drying, the second coat must be smoothed with the blade and re-tightened.

Spray between 60 and 80 of the substrate.

Tools: Airless pump, rotor-stator machine and/or Jet Plat (ideal nozzle 641).

Clean tools with water.

DRYING TIME.

Depends on the substrate, weather conditions and application thickness.

PACKAGING.

25 kg bags.

STORAGE.

18 months in original unopened packaging away from frost and high temperatures.

ADVANTAGES

- Very high filling power.
- Water and moisture resistant.
- Vapour permeable
- Manual or mechanical application.

VOC content <1g/L.

